

Fast-Curing Crack Sealant

JTB-505 快干封缝胶



产 品 说 明 书

Product Manual

产品简介

JTB-505 快干封缝胶具有硬度高、固化速度快、粘结力强，易于和混凝土、石材、钢板等基材粘结等特点。

执行标准：GB50367-2006。

Product

JTB-505 Fast-Curing Crack Sealant features high hardness, fast curing

introduction

speed, strong adhesion, and easy bonding with substrates such as concrete, stone, and steel plates.

Execution standard: GB50367-2006.

产品特点

- 硬度高，抛光性佳
- 固化速度快
- 粘结力强
- 易于与混凝土等基材粘结
- 可在低温环境下施工



Product

features

- High hardness, excellent polishability
- Fast curing
- Strong adhesion
- Strong adhesion to concrete & substrates
- Applicable for low-temperature environments

适用范围

- 用于封闭各种混凝土裂缝、钢板及各种砖板的接缝以及用于非重要结构部位的钢筋植入固定。

Scope of

application

- 在混凝土结构裂缝灌浆修补施工中,用于封闭裂缝和粘结底座。
- Sealing cracks in concrete, joints in steel & masonry anchoring rebar in non-structural areas;
- Used in concrete crack grouting for crack sealing and base adhesion.

Fast-Curing Crack Sealant

JTB-505 快干封缝胶



产 品 说 明 书

Product Manual

施工工艺

Construction technology

- **清理基层:** 清除表面沙粒、灰尘、油脂等杂物, 确保基面干净整洁;
 - **配比搅拌:** 取 3 份甲料和 1 份乙料混合并充分搅拌均匀;
 - **施工:** 将搅拌均匀的金砵宝快干封缝胶涂抹在需要施工的裂缝处即可。
- **Clean the base layer:** Remove surface sand particles, dust, grease and other debris to ensure the base surface is clean and tidy.
 - **Mixing ratio:** Take 3 parts of material A and 1 part of material B, mix them thoroughly and stir evenly.
 - **Construction:** Just apply the well-mixed JTB-505 Fast-Curing Crack Sealant to the crack that needs to be treated.

注意事项

Precautions

粘结物表面要清洁、干燥、无疏松、油污等现象;

本品置于火中时, 会发生剧烈反应, 释放出一氧化碳和二氧化碳;

根据实际需要可适量增加或减少固化剂用量, 以控制固化速度;

拌料时随配随用, 不可一次性将甲、乙料全部混合;

若一次未用完, 则用后必须将盖子盖好, 以便下次再用。

The surface of the bonded material should be clean, dry, free of looseness, oil stains and other phenomena.

When this product is placed in fire, it will undergo a violent reaction, releasing carbon monoxide and carbon dioxide.

The amount of curing agent can be appropriately increased or decreased according to actual needs to control the curing speed.

When mixing the materials, use them immediately after preparation. Do not mix all materials A and B at once.

If it is not used up in one go, the lid must be tightly closed after use for the subsequent use.

Fast-Curing Crack Sealant

JTB-505 快干封缝胶



产 品 说 明 书

Product
Manual

包装与储存	本品包装规格为:每组 10 公斤+0.2 公斤。 本品密封, 储存于阴凉处, 保质期为 12 个月。
Packaging and Storage	The packaging specification of this product is: 10 kg +0.2 kg per set. This product should be sealed and stored in a cool place. Its shelf life is 12 months.

安全规范	施工时应佩戴好口罩、护目镜和手套; 如果接触到皮肤或眼睛, 立即用大量清水冲洗, 情况特别严重时应及时就医。
Safety specification	When working, masks, goggles and gloves should be worn properly. If it comes into contact with the skin or eyes, rinse immediately with plenty of water. Seek medical attention promptly if the situation is particularly serious.



产品施工视频

Product construction video



企业公众号

Enterprise Official Account

Service Hotline: 400-772-5558